

Moisture cured resin for three proof adhesive

Product Code	Active ingredient %	Viscosity (tube viscometer/25 °C)	NCO %	Solvent	Properties
PJ9880-100	100	10000-30000 (mPa·s)	9.5±1	/	UV, Moisture double curing resin, good stability, good electrical performance, moisture and mold resistance
PJ6813-60A	60±2	3-18	5±1	PMA、EAC	Low odour, good substrate adaptability, good adhesion, good flexibility and chemical resistance
PJ6803-60-1	60±2	5-20	6±1	PMA、DMC、EAC	Low odour, good salt mist resistance, fast drying and good flexibility
PJ6803-60-2	60±2	7-28	6±1	PMA	Low odour, high hardness, good levelling and flexibility
PJ6833-70	70±2	25-55	3.8±1	PMA、DMC	High solid content, low odor, mainly diluted with environmental protection solvents D30 and D40, fast drying, good adhesion, good electrical performance
*PJ780-60	60±2	100-400 (mPa·s)	/	PM	Low viscosity, fast surface drying speed, good adhesion on metal, glass and other base materials; high hardness and good gloss